



## Suprasil® 310 – Premium Synthetic Quartz Glass Tubes for Deep UV Applications

Disinfection and cleaning with ultraviolet light is a cost-effective and environmentally friendly alternative to conventionally used chemical processes. Especially the deep UV radiation is becoming a more and more important tool in modern industrial applications. In LCD and semiconductor industries high energy 172 nm UV radiation is used for surface cleaning and processing of wafers and flat panel displays. Other application examples for 172 nm radiation are photochemical vapour deposition, surface activation and photochemistry. The materials specialist Heraeus provides premium synthetic quartz glass especially for deep UV applications.


### **Heraeus features:**

- full synthetic quartz glass tubes for 172 nm applications (furnace cut, machine cut, fire polished, domed)
- highest transmission
- longest lifetime
- outstanding chemical purity
- technical product support
- flexible order quantities
- customized tube size: OD 3 – 350 mm diameter

# Suprasil® 310


## Typical transmission spectrum of Suprasil® 310

thickness: 2 mm



Heraeus provides premium quartz glass tubes for UV and deep UV applications with superior visual quality. These tubes have a superior transmission and a significantly improved lifetime compared to standard natural quartz glass tubes. Supporting highest UV output over a very long operation time Heraeus synthetic tubes provide highest reliability for your products and lower operational costs.

## Transmission of different quartz glass types at 172 nm as a function of irradiation time



## Typical impurity content in weight ppm (µg/g)

Li	Na	K	Mg	Ca	Fe
<0.01	<0.05	<0.01	<0.005	<0.05	<0.02
Cu	Cr	Mn	Al	Ti	
<0.01	<0.005	<0.005	<0.05	<0.05	

A. Schreiber, B. Kühn, E. Arnold, F.-J. Schilling, H.-D. Witzke, Radiation resistance of quartz glass for VUV discharge lamps, J. Phys. D: Appl. Phys. 38 (2005) 3242-3250

## Suprasil® 310 features

Wavelength range	> 160 nm
Optical transmission	Outstanding transmission in the deep UV < 200 nm (80% @ 172 nm for 2 mm thickness)
Resistance to deep UV radiation	Withstands even aggressive 172 nm radiation
Application examples	Lamp envelopes and sleeves for: <ul style="list-style-type: none"> <li>■ Cleaning of surfaces, e.g. in processing of semiconductor wafers and flat panel displays</li> <li>■ Photochemical vapour deposition</li> <li>■ Activation of surfaces</li> <li>■ Changes in structure and composition of surfaces</li> <li>■ Photochemistry</li> </ul>
Lamp types	<ul style="list-style-type: none"> <li>■ 172 nm excimer lamps</li> <li>■ deep UV lamps</li> </ul>
Visual quality	Outstanding visual quality, almost free of any bubbles and inclusions
Availability/MOQ	10 kg

Germany

### Heraeus Quarzglas GmbH & Co. KG

Lamp Materials  
Reinhard-Heraeus Ring 29  
D-63801 Kleinostheim  
Phone +49 (6181) 35-62 48  
Fax +49 (6181) 35-72 00  
E-mail:  
sales.hqs.lampmaterials.de@heraeus.com

China

### Heraeus ShinEtsu Quartz, Inc.

QianJiang Tower,  
20th Floor, Room A  
No. 971 Dongfang Road  
200122 Shanghai  
Phone +86 (21) 68672266-809  
Fax +86 (21) 68751434  
E-mail: sales.hqs.lampmaterials.cn@heraeus.com

USA

### Heraeus Quartz America, LLC.

Sales Lamp Materials  
100 Heraeus Blvd.  
Buford, GA 30518  
Phone +1 (678) 714-4350  
Fax +1 (678) 714-4353  
E-mail: sales.hqs.lampmaterials.us@heraeus.com

UK

### Heraeus Quarzglas GB

4 Tannery House  
Tannery Lane  
Send, Woking  
Surrey GU23 7EF  
Phone +44 (1483) 213324  
Fax +44 (1483) 213329  
E-mail: sales.hqs.lampmaterials.uk@heraeus.com